



Options include: Individually wrapped
Nylon cord handle
Core spool

Nature's Blanket 400 gram coir blanket (NB400)

Quality Code	:	Coir Mat 400
Width(M)	:	2Mtr or 4Mtr
Length(M)	:	50Mtr or 50Mtr
Weight/Roll(KG)	:	40 Kgs 80Kgs
Area/Roll(m2)	:	100M2 200M2
Yarn	:	Wheel Spun, well cleaned, evenly spun and uniformly Twisted
Material	:	100% Spun Coir
Weight(g/m2)ASTM-3776	:	400M2 400M2
Open Area %	:	65% 65%
Wide Width Tensile, Dry(KN/M)	:	
Warp x Fill	:	ASTM 4595 8.9 x 5.4
Wide Width Tensile, Wet(KN/M)	:	
Warp x Fill	:	ASTM 4595 6.6 x 4.2
Elongation at failure, Dry(%)	:	
Warp x Fill	:	ASTM 4595 35 x 30
Elongation at failure, Wet(%)	:	
Warp x Fill	:	ASTM 4595 47 x 44
"C" Factor, 1.5 : 1 slope	:	NA
Water Flow Velocity(m/sec)	:	2.4

www.EcoGro.net

(859) 231-0500 P.O. Box 22273, Lexington, KY 40522

Nature's Blanket 700 gram coir blanket (NB700)

Quality Code	:	Coir Mat 700
Width(M)	:	2Mtr or 4Mtr
Length(M)	:	50Mtr or 50Mtr
Weight/Roll(KG)	:	70 Kgs 140Kgs
Area/Roll(m2)	:	100M2 200M2
Yarn	:	Wheel Spun, well cleaned, evenly spun and uniformly Twisted.
Material	:	100% Spun Coir
Weight(g/m2)ASTM-3776	:	700M2 700M2
Open Area %	:	50% 50%
Wide Width Tensile, Dry(KN/M)	:	
Warp x Fill	:	ASTM 4595 19.6 x 9.5
Wide Width Tensile, Wet(KN/M)	:	
Warp x Fill	:	ASTM 4595 15.1 x 7.2
Elongation at failure, Dry(%)	:	
Warp x Fill	:	ASTM 4595 51 x 36
Elongation at failure, Wet(%)	:	
Warp x Fill	:	ASTM 4595 64 x 48
"C" Factor, 1.5 : 1 slope	:	0.003
Water Flow Velocity(m/sec)	:	3.0

Nature's Blanket 900 gram coir blanket (NB900)

Quality Code	:	Coir Mat 900
Width(M)	:	2Mtr or 4Mtr
Length(M)	:	50Mtr or 50Mtr
Weight/Roll(KG)	:	90 Kgs 180Kgs
Area/Roll(m2)	:	100M2 200M2
Yarn	:	Wheel Spun, well cleaned, evenly spun and uniformly Twisted.
Material	:	100% Spun Coir
Weight(g/m2)ASTM-3776	:	900M2 900M2
Open Area %	:	39% 39%
Wide Width Tensile, Dry(KN/M)	:	
Warp x Fill	:	ASTM 4595 27.8 x 9.3
Wide Width Tensile, Wet(KN/M)	:	
Warp x Fill	:	ASTM 4595 21.4 x 6.8
Elongation at failure, Dry(%)	:	
Warp x Fill	:	ASTM 4595 68 x 32
Elongation at failure, Wet(%)	:	
Warp x Fill	:	ASTM 4595 82 x 49
"C" Factor, 1.5 : 1 slope	:	0.002
Water Flow Velocity(m/sec)	:	4.6



www.EcoGro.net

(859) 231-0500 P.O. Box 22273, Lexington, KY 40522